


PRODUCT DESCRIPTION & USE

Armstead Trade Contract Matt is a professional quality, high opacity, quick drying matt emulsion for both old and new surface areas. Suitable for all normal interior wall and ceiling surfaces.

KEY BENEFITS

- **Excellent coverage**
- **Quick drying**
- **Ideal for new plaster**

PACK SIZES



(Not all colours available in both pack sizes)

COLOUR RANGE

| | |
|----------------------------------|----------------------------------------------------------------------------|
| Armstead Trade Exclusive: | 64 colours |
| BS4800: | 35 colours |
| RAL: | 6 colours |
| NCS 1 & 2: | 64 colours |
| | Visit www.armsteadtrade.co.uk |

FILM PROPERTIES

| | |
|-----------------------------|-------------------------------------------------------------------------------------------|
| Chemical Resistance: | Not suitable. |
| Heat Resistance: | Not suitable for use on heated surfaces e.g. radiators. |
| Water Resistance: | Will tolerate the levels of atmospheric humidity present in normal interior environments. |

COMPOSITION (NOMINAL)

| | |
|-----------------|-----------------------------|
| Pigment: | Lightfast Pigments. |
| Binder: | Acrylic Copolymer Emulsion. |
| Solvent: | Water. |

VOLUME SOLIDS

30% (nominal).

SURFACE PREPARATION

Surfaces must be sound, clean, dry and free from all defective or poorly adhering material, dirt, grease and salts. New plaster and masonry must be fully dry before priming.

APPLICATION



Brush, roller, spray & airless spray.

As with other water-based paints, do not apply in temperatures below 8°C (as recommended by British Standard BS 6150)

SYSTEM INFORMATION

Stir thoroughly before use. On very absorbent surfaces apply a sealing coat of thinned **Armstead Trade Contract Matt**.
Finishing: Apply 1 or 2 coats of **Armstead Trade Contract Matt**.
Note: Special precautions should be taken during surface preparation of pre-1960s paint surfaces over wood and metal as they may contain harmful lead.

PRACTICAL COVERAGE



A guide to the practical coverage which can be achieved under normal conditions is up to 15m²/litre.

THINNING

| | |
|-----------------------------------------|------------------------------------------------|
| Sealing new/bare surfaces: | Add up to 1 part clean water to 5 parts paint. |
| Normal use (not to be exceeded): | Thinning is not required. |
| Conventional spray application: | Add up to 1 part clean water to 5 parts paint. |
| Airless spray application: | Thinning is not required. |

SPRAY RECOMMENDATIONS

| | |
|----------------------------|--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Conventional Spray: | Satisfactory through most equipment. |
| Airless Spray: | A typical recommendation for airless spray application is a minimum working pressure on paint of 140 kg/cm ² (2000 lb/sq in) with a spray tip size of 0.38mm (15 thou) spray tip Angle 65°. |

DRYING TIMES (SINGLE COAT, STANDARD THICKNESS)



| | |
|-------------------|------------|
| Touch Dry: | 1-2hours* |
| Recoat: | 2-4 hours* |

*Dependent upon temperature and humidity.

CLEANING UP



After use, remove as much paint as possible from equipment before cleaning with clean water.

TRANSPORTATION & STORAGE

Do not use or store in extremes of temperature and protect from frost. To prevent spillage, please store and transport upright.

VOC

EU limit value for this product (cat A/a) : 30g/l (2010). This product contains max. 2.9g/l VOC

VOC Content Minimal 0 – 0.29%. VOCs (Volatile Organic Compounds) contribute to atmospheric pollution.

FURTHER SUPPORT

Online: www.armsteadtrade.co.uk
Email: armstead.advice@akzonobel.com
Phone: 0333-222-70-70
Please visit www.armsteadtrade.co.uk to download safety sheet SDSAM201



Like us on Facebook



Videos on YouTube



Follow us on Twitter



Let's create together a better future for our planet.
Find out how at: www.armsteadtrade.co.uk/pp